

DESCRIPTION

White matte textured decorative plaster. Speckled with small white grains, it helps mask minor surface irregularities.



USE

- Interior plaster for walls and ceilings on all common substrates.

TECHNICAL SPECIFICATIONS

TYPICAL SPREADABILITY:

0.7 to 1 kg/m² depending on the desired effect.

DENSITY:

1,7 +/- 0,1 kg/l

SOLID CONTENT:

- Solid content by weight: 71%
- Solid content by volume: 51%

APPLICATION CONDITIONS:

- +8°C to +35°C
- Maximum humidity 70% RH

PH:

8 ± 1

CLEANING TOOLS:

With water

RECOMMENDED THICKNESSES:

- Minimum thickness: 0.3 mm
- Maximum thickness: 2 mm

DRYING:

- Approximately 24 hours depending on application thickness, temperature, ventilation, humidity, and substrate type. Sanding and covering: after complete drying.

PACKAGING AND STORAGE

- 25 kg plastic bucket.

- Shelf life of 1 year in unopened original packaging, protected from frost and excessive heat.

METHOD OF APPLICATION

SUBSTRATES:

- On powdery substrates, apply a fixer. Plaster, plaster tiles, plasterboard, cement coating, old substrates, old paints, printed wood.

ENVIRONMENTAL INFORMATION

- Teneur en COV : < 1 g/l.
- Indoor Air Emission Class



CHARACTERISTICS

- Fire classification: A2-s1, d0 according to European standard EN 13501-1.
- Classification: family III class 2 according to AFNOR NF T 36-005, compliant with AFNOR standard NF T 30-608.

PREPARATION OF SUBSTRATE:

- The supports, preparatory work, and conditions of application will be in accordance with the DTU and current standards.

APPLICATION TIPS:

- Mix before use if necessary.
- Applicable to the projection machine, pressure pots, gravity gun.

RECOMMENDATIONS:

- Ventilate the room during application and drying.
- Use clean and properly maintained PPE: gloves and eye protection designed against liquid splashes, mask during sanding operations.
- To clean tools, scrape off excess and immerse in a minimum amount of water.
- Do not dispose of residues in the sewer. Dispose of contents/container at a hazardous or special waste collection center.
- Conserver à l'abri du gel et de la chaleur.
- Tightly reseal the container after use.
- Ensure adequate ventilation to remove excess humidity and speed up drying.

HEALTH AND SAFETY

The safety data sheet is available on the website: <https://icp-alltek.com/en-gb/documentation/>