

DESCRIPTION

Lightweight filling compound, low-shrinkage ready-mixed paste. Quick and easy roller application. The 17L (4.5 gal) bucket delivers superior coverage — ideal for use with a wide roller on large surface areas.

USE

- Interior plaster for walls and ceilings on all common substrates.
- Surface renovation for smooth coats on glass fiber or droplet-textured wall coverings.
- Easy application with roller and smoothing.
- Suitable for application in thick layers.



TECHNICAL SPECIFICATIONS

TYPICAL SPREADABILITY:

1 litre/m² per mm thickness.

DENSITY:

1,1 +/- 0,1 kg/l

SOLID CONTENT:

- Solid content by weight : 61%
- Solid content by volume : 55%

APPLICATION CONDITIONS:

- +8°C à +35°C
- Maximum humidity 70% RH

PH :

8.5 +/- 1.0

CLEANING TOOLS:

With water

RECOMMENDED THICKNESSES:

- Minimum thickness: 0.5 mm
- Maximum thickness: 4 mm

DRYING :

- Approximately 24 hours depending on application thickness, temperature, ventilation, humidity, and substrate type.
- Sanding and covering: after complete drying.

PACKAGING AND STORAGE

- 12-liter plastic bucket (réf. 103579).
- 17-liter plastic bucket (réf. 103580).
- Shelf life of 1 year in unopened original packaging, protected from frost and excessive heat.

ENVIRONMENTAL INFORMATION

- Teneur en COV : < 1 g/l.
- Indoor Air Emission Class



CARACTÉRISTIQUES

- Fire classification: A2-s1, d0 according to European standard EN 13501-1.
- Classification: family III class 2 according to AFNOR standard NF T 36-005.
- Product compliant with standard NF EN 16566.

METHOD OF APPLICATION

SUBSTRATES :

- Concrete, brick, and terracotta tile, plaster, plaster block, plasterboard (drywall).
- For renovation: over fibreglass wall covering (glass fabric) or textured/structured coatings.
- Wood and wood-based panels (previously primed), and old paint coatings that are sound and well-adhered.

PREPARATION OF SUBSTRATE:

- The supports, preparatory work, and conditions of application will be in accordance with the DTU and current standards.

APPLICATION TIPS:

- Mix/stir before use if necessary, and dip a black-fibre polyamide roller (180 to 300 mm) into the coating, then apply generously to the substrate.
- Smooth the coating using a flexible blade spatula.
- Sanding with grit P150 to P220.

RECOMMANDATIONS :

- Ventilate the room during application and drying.
- Use clean, properly maintained PPE: gloves and eye protection designed against liquid splashes, and a mask during sanding operations.
- To clean tools, scrape off excess product and soak in a minimum amount of water.
- Do not dispose of residues down the drain. Dispose of contents/container at a hazardous or special waste collection facility.
- Store away from frost and heat.
- Reseal the container tightly after use.
- Ensure adequate ventilation to remove excess moisture and speed up drying.

HEALTH AND SAFETY

The safety data sheet is available on the website: <https://icp-alltek.com/en-gb/documentation/>